

**ATTAR**

Advanced Technology Testing and Research

ATTAR TEST REPORT NUMBER: 16/9799.3
Replacement of ATTAR Test Report No. 15/9095.3



The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.
 Accredited for compliance with ISO/IEC 17025.
 Accreditation Number: 2735

4 February 2016

Total Pages: 2**OIL-WET INCLINING PLATFORM SLIP RESISTANCE**

Job No: M16/9799

Prepared for:	Godfrey Hirst 7 Factories Road SOUTH GEELONG VIC 3220	
Attention:	Mandy Chandley	
Test Site:	ATTAR, Unit 1, 64 Bridge Road, Keysborough.	
Test Date:	9 July 2015	
Manufacturer:	Unknown	
Test Specimen, Size & Quantity:	GH LVP Orion and Vega, 25x152 cm, 5 off supplied.	
Sampling & Direction of Testing:	Sampling conducted by client. Test direction parallel with grain profile. Refer to Figure 1.	
Test Personnel:	Darryl Pierce & Douglas Lehne.	
Preparation:	Washed with water and pH neutral detergent, rinsed with water, then dried.	
Joint Width:	N/A	
Air Temperature:	22°C	
Test Standard:	AS 4586 - 2013 Slip resistance classification of new pedestrian surface materials – Appendix D.	
Surface Structure :	Structured.	
Test Shoes:	Lupos Picasso	
Classification Criteria: (TABLE 5 in AS 4586 - 2013)	Classification	Angle, degrees
	No Classification	<6
	R9	≥6<10
	R10	≥10<19
	R11	≥19<27
	R12	≥27<35
	R13	≥35
Displacement Space:	Not Measured	
Displacement Space Assessment Group:	N/A	
Corrected Mean Overall Acceptance Angle (rounded down to the nearest degree):	10°	
Classification:	R10	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in one (1) months time, unless otherwise instructed.

ATTAR

Douglas Lehne
 Slip Testing Technician
 Approved Signatory

Reviewed by:

Marcus Braché
 Senior Engineering Technician
 Approved Signatory

This report may not be reproduced except in its entirety.

Page 1 of 2

ATTAR - Advanced Technology Testing and Research
 A division of Engineering Materials Evaluation Pty Ltd ABN 14 006 554 785

Unit 1, 64 Bridge Road, Keysborough Victoria 3173 T (03) 9574 6144 F (03) 9574 6133 E admin@attar.com.au www.attar.com.au

ATTAR TEST REPORT NUMBER: 16/9799.3
Replacement of ATTAR Test Report No. 15/9095.3

4 February 2016

Total Pages: 2



Figure 1: GH LVP Orion and Vega.
Arrow indicates direction of test.