

**ATTAR**

Advanced Technology Testing and Research

ATTAR TEST REPORT NUMBER: 16/9799.2
Replacement of ATTAR Test Report No. 15/9095.2



The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.
 Accredited for compliance with ISO/IEC 17025.
 Accreditation Number: 2735

4 February 2016

Total Pages: 2**WET PENDULUM SLIP RESISTANCE**

Job No: M16/9799

Prepared for:	Godfrey Hirst 7 Factories Road SOUTH GEELONG VIC 3220					
Attention:	Mandy Chandley					
Test Site:	ATTAR, Unit 1, 64 Bridge Road, Keysborough.					
Test Date:	29 June 2015					
Test Specimens, Size & Quantity:	GH LVP Orion and Vega, 25x152 cm, 5 off supplied.					
Sampling & Direction of Testing:	Sampling conducted by client. Test direction parallel with grain profile. Refer to Figure 1.					
Test Personnel:	Darryl Pierce					
Preparation:	Washed with water and pH neutral detergent, rinsed with water, then dried.					
Fixed/Unfixed:	Unfixed.					
Air Temperature:	22°C					
Test Equipment:	Munro Stanley Skid Resistance Tester (Pendulum) Serial Number 0320, Calibrated 16/10/2013.					
Test Standard:	AS 4586: 2013 Slip resistance classification of new pedestrian surface materials – Appendix A.					
Slider Rubber:	Slider 96 Batch No. #59 prepared on P400 & 3µm lapping film.					
Classification Criteria:	Refer to Classification Criteria, attached as Appendix 1.					
British Pendulum Number	Specimen Number					SRV*
	1	2	3	4	5	
	41	35	41	37	37	38
Classification:	P3					

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

* Slip Resistance Value.

NOTE: Any specimens supplied will be disposed of in one (1) months time, unless otherwise instructed.

ATTAR

Douglas Lehne
 Slip Testing Technician
 Approved Signatory

Reviewed by:

Marcus Braché
 Senior Engineering Technician
 Approved Signatory

This report may not be reproduced except in its entirety.

Page 1 of 2

ATTAR TEST REPORT NUMBER: 16/9799.2
Replacement of ATTAR Test Report No. 15/9095.2

4 February 2016

Total Pages: 2



Figure 1: GH LVP Orion and Vega.
Arrow indicates direction of test.